

TintCrete Concrete Resurfacer

STEP-BY-STEP INSTRUCTIONS



Preparation for Application

1. Surface prep is key to a long lasting repair.
2. Clean existing surface. Surface should be sound and free of oils, curing compounds, dust or any other foreign matters.
3. Immediately prior to product placement, the surface to be repaired or resurfaced should be moist with potable water and free of any standing water.
4. If possible, apply first thing in the morning or last part of the afternoon to avoid rapid drying.

Mixing Guidelines

1. Start with 1 part water and add 2 parts powder and then mix to a lump-free consistency. ****INCONSISTENT WATER CONTENT WILL CAUSE VARIATION IN COLOR. FOR CONSISTENT COLOR, ALWAYS USE THE SAME AMOUNT OF POTABLE WATER IN THE MIX. APPLY TO A TEST AREA PRIOR TO FINAL APPLICATION TO ASSURE COLOR AND FINISHING TECHNIQUE DESIRED.****
2. Add up to 1 additional part powder to thicken the product.
3. Continue mixing until you reach the desired lump-free application consistency.
4. For patching and tuck-pointing, a stiffer consistency is typically preferred.
5. Remember, any additional powder you add will darken the final color, and less powder will lighten the final color.
6. Apply the product when the temperature is over 45 °F and under 90 °F.

Application

1. For all applications, rub or scratch part of the mixed material onto surface just prior to application.
2. Apply mixed material up to 1/4".
3. For thickness over 1/4", apply in multiple applications.
4. Finish with trowel, broom, brush, float or sponge.
5. For a finer finish, use a finer broom or brush.
6. ****If the material is placed in a joint or crack, that has movement, expect the product to crack due to the movement.**

Curing

1. Product sets in approximately 1 hour. Depending on the weather and application area, repair area may be ready for light traffic in 6 to 8 hours at 70°F.
2. Rapid drying of cement-based products may cause cracking or de-bonding. Avoid applications in direct sunlight, high winds, excessive heat or blowing air directly on freshly placed product.

LIMITED WARRANTY JE Tomes & Associates, Inc. warrants its products to be free from manufacturing defects and will deliver, at no charge, an equal amount of packaged product as that amount proven to be defective when applied in accordance with manufacturer's written directions by contractors experienced in this application, and used in applications recommended by the manufacturer as suitable for the product. All claims concerning product defects must be made within twelve (12) months of use of the product. **THERE ARE NO OTHER WARRANTIES BY JE TOMES & ASSOCIATES, INC. OF ANY NATURE WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH PRODUCTS WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** Buyer's sole and exclusive remedy for breach of any warranty shall be replacement of defective product. JE Tomes & Associates, Inc. shall not be liable for any damages, including consequential damages, except as otherwise set forth therein.

Product Description

TintCrete Resurfacer 100 is a special blend of cements, aggregates and exclusive modifiers. Our concrete resurfacer is designed for general-purpose and high-performance concrete resurfacing or repair applications. TintCrete Resurfacer comes in two colors. New Concrete Color, a light-grey color, designed to match your new concrete. Old Concrete Color, a beige color, designed to match aged concrete and keep a consistent color throughout your property.

Features

- Easy to use
- Just add Water
- Portland Cement Based
- Self-Curing, Self Bonding
- Long Lasting
- Durable
- Available in New Concrete color and Aged (Old) Concrete color

Where to Use:

- Flatwork (Slabs, Driveways, Sidewalks, Patios, Garage Floors, Basement Floors and more)
- Stoops and Stairs
- Concrete Walls
- Interior and exterior use

Packaging and Yield

- Available In:

3 lbs	6 sq.ft
10 lbs	20 sq.ft
50 lbs	100 sq.ft @1/16" thickness